

L5 ANSWER 48 OF 575 CA COPYRIGHT 2004 ACS on STN
 AN 137:51060 CA
 ED Entered STN: 18 Jul 2002
 TI Manufacture of **composition** for preparing cellular **fly ash**-concrete for walls and heat-insulating structures
 IN Belov, V. V.; Kulagin, Yu. V.; Gevorkyan, V. A.
 PA Russia
 SO Russ., No pp. given
 CODEN: RUXXE7
 DT Patent
 LA Russian
 IC ICM C04B038-02
 ICS C04B040-00
 CC 58-2 (Cement, Concrete, and Related Building Materials)
 FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	RU 2168485	C1	20010610	RU 2000-102081	20000131
PRAI	RU 2000-102081		20000131		

AB The compn. comprises **cement** 25.6-32.8, **fly ash** from thermoelec. plant 32.7-41, sodium sulfate 0.51-0.66, foaming agent (e.g., aluminum powder) 0.1-0.26, and tempering **water** in the balance. Sodium sulfate is used as alkali additive and hardening agent. The manuf. comprises (a) prepg. a viscous raw mix of components, (b) pre-activating **fly ash**, (c) swelling raw mix, (d) hardening during evapn. or under normal conditions, and (e) activating **fly ash** by combined grinding of all dry mix components for 20-40 min. Prior to grinding, dry superplasticizer S-3 in amt. of 0.7-1% of **cement** wt. is added into the mix, and sulfanol surfactant is added into tempering **water** in amt. of 0.2-0.5% of **water**. The method improves properties of the compn.
 ST cellular concrete **cement fly ash** thermal insulator wall